

TEST REPORT

Report No.:TBR-C-202504-0037-6

Page 1 of 12

Applicant Company : Shenzhen Domino Times Technology Co.,Ltd
Room806, Taibang Technology Building, Suite 16, GaoxinSouth 6th
Address : Road, High-Tech community, Yuehai Street,Nanshan District, Shenzhen,
China
Manufacturer : Shenzhen Domino Times Technology Co.,Ltd
Room806, Taibang Technology Building, Suite 16, GaoxinSouth 6th
Address : Road, High-Tech community, Yuehai Street,Nanshan District, Shenzhen,
China

Sample Information


Sample Name : GPS Smart Watch
Trade Mark : /
Basic Model No. : DM76
Series Model No. : /
Sample Received Date : May 13, 2025
Testing Period : May 13, 2025~May 19, 2025
Date of issue : May 19, 2025
Results : Please refer to next page(s).

TEST REQUEST	CONCLUSION
As specified by client, based on the performed tests on submitted sample, the result of Lead(Pb), Cadmium(Cd), Mercury(Hg), Hexavalent Chromium(Cr(VI)), PBBs, PBDEs, Dibutyl Phthalate(DBP), Butylbenzyl Phthalate(BBP), Di-2-ethylhexyl Phthalate(DEHP) and Diisobutyl phthalate(DIBP) content comply with the limits set by RoHS Directive 2011/65/EU with amendment (EU) 2015/863.	Pass

Edited by:

Wick Wu

Approved by:



Shenzhen Toby Laboratories Inc.

Rm.307-309, 311, Bldg.2, Huahan Sci-tech Industrial Park, No.19 Lanjin 4th Road, Heping Community,
Pingshan St., Pingshan District, Shenzhen, Guangdong, China

Tel: (86) 0755-28681336 toby@toby-lab.cn Http://www.toby-lab.cn

TEST REPORT

Report No.:TBR-C-202504-0037-6

Page 2 of 12

TEST RESULTS:

1. Screening test

Test method: With reference to IEC 62321-3-1:2013 and IEC 62321-8:2017. For Heavy Metals and Flame Retardants, analyzed by Energy Dispersive X-ray Fluorescence Spectrometer (XRF); for phthalates, analyzed by Gas Chromatography and Mass Spectrometer (GC-MS).

Sample No.	Sample Description	Heavy Metals and Flame Retardants					Phthalates			
		Cd	Pb	Hg	Cr [▼]	Br [▼]	DIBP	DBP	BBP	DEHP
1	Golden metal shell	BL	BL	BL	BL	N/A	N/A	N/A	N/A	N/A
2	Black metal shell	BL	BL	BL	BL	N/A	N/A	N/A	N/A	N/A
3	Silver metal shell	BL	BL	BL	BL	N/A	N/A	N/A	N/A	N/A
4	White rubber strap	BL	BL	BL	BL	BL	BL	BL	BL	BL
5	Grey rubber strap	BL	BL	BL	BL	BL	BL	BL	BL	BL
6	Grey rubber strap	BL	BL	BL	BL	BL	BL	BL	BL	BL
7	White plastic shell	BL	BL	BL	BL	BL	BL	BL	BL	BL
8	Black plastic shell	BL	BL	BL	BL	BL	BL	BL	BL	BL
9	White ribbon	BL	BL	BL	BL	BL	BL	BL	BL	BL
10	Black Velcro loop	BL	BL	BL	BL	BL	BL	BL	BL	BL
11	Grey ribbon	BL	BL	BL	BL	BL	BL	BL	BL	BL
12	White plastic shell	BL	BL	BL	BL	BL	BL	BL	BL	BL
13	Grey ribbon	BL	BL	BL	BL	BL	BL	BL	BL	BL
14	Black ribbon	BL	BL	BL	BL	BL	BL	BL	BL	BL
15	Black plastic shell	BL	BL	BL	BL	BL	BL	BL	BL	BL
16	Yellow metal contact	BL	BL	BL	X	N/A	N/A	N/A	N/A	N/A
17	Black plastic sheet	BL	BL	BL	BL	BL	BL	BL	BL	BL
18	White plastic shell	BL	BL	BL	BL	BL	BL	BL	BL	BL
19	Black plastic shell	BL	BL	BL	BL	BL	BL	BL	BL	BL
20	Silver metal shell	BL	BL	BL	X	N/A	N/A	N/A	N/A	N/A
21	Black metal shell	BL	BL	BL	X	N/A	N/A	N/A	N/A	N/A
22	Golden metal shell	BL	BL	BL	X	N/A	N/A	N/A	N/A	N/A
23	Black LCD screen	BL	BL	BL	BL	BL	BL	BL	BL	BL
24	Silver tape	BL	BL	BL	BL	BL	BL	BL	BL	BL
25	Yellow tape	BL	BL	BL	BL	BL	BL	BL	BL	BL



Shenzhen Toby Laboratories Inc.

Rm.307-309, 311, Bldg.2, Huahan Sci-tech Industrial Park, No.19 Lanjin 4th Road, Heping Community, Pingshan St., Pingshan District, Shenzhen, Guangdong, China

Tel: (86) 0755-28681336 toby@toby-lab.cn Http://www.toby-lab.cn

TEST REPORT

Report No.:TBR-C-202504-0037-6

Page 3 of 12

Sample No.	Sample Description	Heavy Metals and Flame Retardants					Phthalates			
		Cd	Pb	Hg	Cr ^{VI}	Br ^{VI}	DIBP	DBP	BBP	DEHP
26	Solder	BL	BL	BL	BL	N/A	N/A	N/A	N/A	N/A
27	Silver metal shell	BL	BL	BL	BL	N/A	N/A	N/A	N/A	N/A
28	Blue PCB board	BL	BL	BL	BL	X	BL	BL	BL	BL
29	Black plastic shell	BL	BL	BL	BL	BL	BL	BL	BL	BL
30	Black line skin	BL	BL	BL	BL	BL	BL	BL	BL	BL

NOTE :

- "BL" denotes below limit
- "OL" denotes over limit, further confirmation test was conducted
- "X" denotes inconclusive, further confirmation test was conducted
- "NA" denotes not applicable
- As requested by the applicant, only the selected components listed in this report were tested.

Remark :

- 1) Results were obtained by XRF for primary screening, and further chemical testing by ICP(for Cd, Pb, Hg), UV-Vis(for Cr(VI)) and GC-MS(for PBBs, PBDEs) are recommended to be performed, if the concentration exceeds the below warning value according to IEC 62321-3-1:2013(Unit: mg/kg).

Element	Polymers	Metals	Composite material
Cd	$BL \leq (70-3\sigma) < X < (130+3\sigma) \leq OL$	$BL \leq (70-3\sigma) < X < (130+3\sigma) \leq OL$	$LOD < X < (150+3\sigma) \leq OL$
Pb	$BL \leq (700-3\sigma) < X < (1300+3\sigma) \leq OL$	$BL \leq (700-3\sigma) < X < (1300+3\sigma) \leq OL$	$BL \leq (500-3\sigma) < X < (1500+3\sigma) \leq OL$
Hg	$BL \leq (700-3\sigma) < X < (1300+3\sigma) \leq OL$	$BL \leq (700-3\sigma) < X < (1300+3\sigma) \leq OL$	$BL \leq (500-3\sigma) < X < (1500+3\sigma) \leq OL$
Cr	$BL \leq (700-3\sigma) < X$	$BL \leq (700-3\sigma) < X$	$BL \leq (500-3\sigma) < X$
Br	$BL \leq (300-3\sigma) < X$	/	$BL \leq (250-3\sigma) < X$

- 3σ = The reproducibility of analytical instruments
- "/" = Not applicable
- LOD = Detection limit

- 2) The XRF screening test for RoHS elements – The reading may be different to the actual content in the sample be of non-uniformity composition.



Shenzhen Toby Laboratories Inc.

Rm.307-309, 311, Bldg.2, Huahan Sci-tech Industrial Park, No.19 Lanjin 4th Road, Heping Community, Pingshan St., Pingshan District, Shenzhen, Guangdong, China

Tel: (86) 0755-28681336 toby@toby-lab.cn Http://www.toby-lab.cn

TEST REPORT

Report No.:TBR-C-202504-0037-6

Page 4 of 12

- 3) The maximum permissible limit is quoted from the document RoHS Directive 2011/65/EU with amendment (EU) 2015/863.
- 4) ▼=For restricted substances PBBs and PBDEs, the results show the total Br content, the restricted substance was Cr(VI), and the results showed the total Cr content.
- 5) Screening results of phthalates are for primary screening, and further chemical testing by GC-MS (for DBP, BBP,DEHP and DIBP) are recommended to be performed if the concentration exceeds the below warning value(Unit: mg/kg).

Test item	Screening limit
Di-2-ethylhexyl phthalate(DEHP)	BL≤600<X
Dibutyl phthalate(DBP)	BL≤600<X
Benzylbutyl phthalate(BBP)	BL≤600<X
Diisobutyl phthalate(DIBP)	BL≤600<X

Disclaimers:

This XRF Screening report is for reference purposes only. The applicant shall make its/his/her own judgment as to whether the information provided in this XRF screening report is sufficient for its/his/her purposes. The result shown in this XRF screening report will differ based on various factors, including but not limited to, the sample size, thickness, area, surface flatness, equipment parameters and matrix effect (e.g. plastic, rubber, metal, glass, ceramic etc.). Further wet chemical pre-treatment with relevant chemical equipment analysis are required to obtain quantitative data.



Shenzhen Toby Laboratories Inc.

Rm.307-309, 311, Bldg.2, Huahan Sci-tech Industrial Park, No.19 Lanjin 4th Road, Heping Community, Pingshan St., Pingshan District, Shenzhen, Guangdong, China

Tel: (86) 0755-28681336 toby@toby lab.cn Http://www.toby lab.cn

TEST REPORT

Report No.:TBR-C-202504-0037-6

Page 5 of 12

2. Chemical test for further confirmation.

1) The test results of Hexavalent Chromium(Cr(VI)) (for metal)

Test method: With reference to IEC 62321-7-1:2015, extracted with boiling water and analysis was performed by UV-visible spectrophotometer (UV-Vis)

Tested Items	Unit	LOQ	Results		Limit
			(16)	(20)	
Hexavalent Chromium(Cr(VI)) Content★	µg/cm ²	0.10	Negative	Negative	0.13

Tested Items	Unit	LOQ	Results		Limit
			(21)	(22)	
Hexavalent Chromium(Cr(VI)) Content★	µg/cm ²	0.10	Negative	Negative	0.13

2) The test results of PBBs & PBDEs

Test method: With reference to IEC 62321-6:2015, by solvent extraction and analysis was performed by gas chromatographic-mass spectrometer (GC-MS)

Tested Items	Unit	MDL	Results	Limit
			(28)	
Polybrominated Biphenyls(PBBs) Content				
Monobromobiphenyl	mg/kg	50	N.D.	-
Dibromobiphenyl	mg/kg	50	N.D.	-
Tribromobiphenyl	mg/kg	50	N.D.	-
Tetrabromobiphenyl	mg/kg	50	N.D.	-
Pentabromobiphenyl	mg/kg	50	N.D.	-
Hexabromobiphenyl	mg/kg	50	N.D.	-
Heptabromobiphenyl	mg/kg	50	N.D.	-
Octabromobiphenyl	mg/kg	50	N.D.	-
Nonabromodiphenyl	mg/kg	50	N.D.	-
Decabromodiphenyl	mg/kg	50	N.D.	-
Total content	mg/kg	-	N.D.	1000



Shenzhen Toby Laboratories Inc.

Rm.307-309, 311, Bldg.2, Huahan Sci-tech Industrial Park, No.19 Lanjin 4th Road, Heping Community, Pingshan St., Pingshan District, Shenzhen, Guangdong, China

Tel: (86) 0755-28681336 toby@toby lab.cn Http://www.toby lab.cn

TEST REPORT

Report No.:TBR-C-202504-0037-6

Page 6 of 12

Polybrominated Diphenylethers(PBDEs) Content				
Monobromodiphenyl ether	mg/kg	50	N.D.	-
Dibromodiphenyl ether	mg/kg	50	N.D.	-
Tribromodiphenyl ether	mg/kg	50	N.D.	-
Tetrabromodiphenyl ether	mg/kg	50	N.D.	-
Pentabromodiphenyl ether	mg/kg	50	N.D.	-
Hexabromodiphenyl ether	mg/kg	50	N.D.	-
Heptabromodiphenyl ether	mg/kg	50	N.D.	-
Octabromodiphenyl ether	mg/kg	50	N.D.	-
Nonabromodiphenyl ether	mg/kg	50	N.D.	-
Decabromodiphenyl ether	mg/kg	50	N.D.	-
Total content	mg/kg	-	N.D.	1000

Remark :

- MDL = Method Detection Limit
- “-” = Not Regulated
- N.D.=Not Detected(<MDL or LOQ)
- mg/kg = ppm=parts per million
- LOQ = Limit of Quantification, The LOQ of Hexavalent chromium is 0.10 µg/cm²
- ★ = a. The sample is positive for Cr(VI) if the Cr(VI) concentration is greater than 0.13µg/cm². The sample coating is considered to contain Cr(VI).
b. The sample is negative for Cr(VI) if Cr(VI) is N.D.(concentration less than 0.10µg/cm²). The sample coating is considered a non- Cr(VI) based coating.
c. The result between 0.10µg/cm² and 0.13µg/cm² is considered to be inconclusive, unavoidable coating variations may influence the determination.
- Information on storage conditions and production date of the tested samples is unavailable and thus Cr(VI) results represent status of the sample at the time of testing.



Shenzhen Toby Laboratories Inc.

Rm.307-309, 311, Bldg.2, Huahan Sci-tech Industrial Park, No.19 Lanjin 4th Road, Heping Community, Pingshan St., Pingshan District, Shenzhen, Guangdong, China

Tel: (86) 0755-28681336 toby@toby-lab.cn Http://www.toby-lab.cn

TEST REPORT

Report No.:TBR-C-202504-0037-6

Page 7 of 12

RoHS Restricted Substances	Maximum Concentration Value (mg/kg) (by weight in homogenous materials)
Cadmium(Cd)	100
Lead(Pb)	1000
Mercury(Hg)	1000
Hexavalent Chromium(Cr(VI))	1000
Polybrominated biphenyls(PBBs)	1000
Polybrominated diphenylethers(PBDEs)	1000
Dibutyl Phthalate(DBP)	1000
Butylbenzyl Phthalate(BBP)	1000
Di-(2-ethylhexyl) Phthalate(DEHP)	1000
Diisobutyl phthalate(DIBP)	1000



Shenzhen Toby Laboratories Inc.

Rm.307-309, 311, Bldg.2, Huahan Sci-tech Industrial Park, No.19 Lanjin 4th Road, Heping Community,
Pingshan St., Pingshan District, Shenzhen, Guangdong, China

Tel: (86) 0755-28681336 toby@toby-lab.cn Http://www.toby-lab.cn


TEST REPORT

Report No.:TBR-C-202504-0037-6


Page 8 of 12

Test Process

1. Lead(Pb) & Cadmium(Cd): IEC 62321-5:2013




2. Mercury(Hg): IEC 62321-4:2013+AMD1:2017 CSV



3. Hexavalent Chromium(Cr(VI))

1) IEC 62321-7-2:2017



Shenzhen Toby Laboratories Inc.

Rm.307-309, 311, Bldg.2, Huahan Sci-tech Industrial Park, No.19 Lanjin 4th Road, Heping Community, Pingshan St., Pingshan District, Shenzhen, Guangdong, China


Tel: (86) 0755-28681336 toby@toby lab.cn Http://www.toby lab.cn

TEST REPORT


Report No.:TBR-C-202504-0037-6

Page 9 of 12


2) IEC 62321-7-1:2015



4. Polybrominated Biphenyls(PBBs) & Polybrominated Diphenyl Ethers(PBDEs) : IEC 62321-6:2015



5. Phthalates(DBP, BBP, DEHP & DIBP) : IEC 62321-8:2017



Shenzhen Toby Laboratories Inc.

Rm.307-309, 311, Bldg.2, Huahan Sci-tech Industrial Park, No.19 Lanjin 4th Road, Heping Community, Pingshan St., Pingshan District, Shenzhen, Guangdong, China

Tel: (86) 0755-28681336 toby@toby-lab.cn Http://www.toby-lab.cn

TEST REPORT

Report No.:TBR-C-202504-0037-6

Page 10 of 12

Sample Photo(s)



Shenzhen Toby Laboratories Inc.


Rm.307-309, 311, Bldg.2, Huahan Sci-tech Industrial Park, No.19 Lanjin 4th Road, Heping Community,
Pingshan St., Pingshan District, Shenzhen, Guangdong, China

Tel: (86) 0755-28681336 toby@toby lab.cn Http://www.toby lab.cn

TEST REPORT

Report No.:TBR-C-202504-0037-6

Page 11 of 12



Shenzhen Toby Laboratories Inc.


Rm.307-309, 311, Bldg.2, Huahan Sci-tech Industrial Park, No.19 Lanjin 4th Road, Heping Community,
Pingshan St., Pingshan District, Shenzhen, Guangdong, China

Tel: (86) 0755-28681336 toby@toby-lab.cn Http://www.toby-lab.cn

TEST REPORT

Report No.:TBR-C-202504-0037-6

Page 12 of 12



Statement:

1. The information as listed on the first page of this test report was all provided by the client except the sample from, date received, test period, test results and conclusion. The client shall be responsible for the representativeness of sample and authenticity of materials, for which TOBY shall bear no responsibilities.
2. This test data is only responsible for the tested sample. The judgment method of determining the conformity in this test report is according to the measured value without considering the risk caused by uncertainty, unless otherwise clearly stipulated in special agreement, standard or specification. The client shall assume the risk caused by the judgment method, and TOBY shall not bear related responsibilities.
3. The test report is effective only with both signature and specialized stamp. Without written approval of TOBY, this report can't be reproduced in full or in part.
4. The results in the report if there is no CMA mark are only used for the client's scientific research, teaching, internal quality control etc., and shall not be used as proof of commercial use or legal action.
5. The marked with special symbols in CNAS logo report means that the test item(s) was(were) currently not applying for CNAS accreditation.

***** END OF REPORT *****



Shenzhen Toby Laboratories Inc.

Rm.307-309, 311, Bldg.2, Huahan Sci-tech Industrial Park, No.19 Lanjin 4th Road, Heping Community, Pingshan St., Pingshan District, Shenzhen, Guangdong, China

Tel: (86) 0755-28681336 toby@toby lab.cn Http://www.toby lab.cn